Report Number STL/21/1844

STANDARD TECHNICAL LLP.
F-26, 1ST FLOOR, SECTOR-11, NOIDA
email. lab@standard-technical.com | phone. +91 74281 45627 | web. www.standard-technical.com

Page 1 - 6

TEST REPORT

APPLICANT :

E-25, SECTOR-11, NOIDA

Report Number	STL/21/1844
Report Date	09-08-2021
Sample Received	04-08-2021

ATTN:-   Sunil Dutt

Status   **Pass**

Sample quantity / sample type	: 4 / FACE MASK
Product description	: FACE MASK
End use	: MASK
Style name	: ST ENGINEERING 1 LADIES MASK
Season	: NOT PROVIDED
Buyer	: POP PROMOS
Style number	: 50791
Reference No.	: 50791
Color name / reference	: ST ENGINEERING 1 BLUE
Fiber content	: 100 % COTTON
Country of origin	: INDIA
Country of destination	: USA

Mr Amit Kumar
LAB INCHARGE

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Equivalent color/code
1	WHITE ELASTIC (TIE STRAPS)	ST ENGINEERING 1 BLUE
2	BLACK RUBBER STOPPER	ST ENGINEERING 1 BLUE

STANDARD TECHNICAL LLP.
F-26, 1ST FLOOR, SECTOR-11, NOIDA
email. lab@standard-technical.com | phone. +91 74281 45627 | web. www.standard-technical.com

Page 3 - 6

TEST SUMMARY

Test Parameters	Pass	Fail	Remarks
CPSIA Section 101, Total Lead in Substrate Materials	X	-	-
California Proposition 65, Total Lead in Substrate Materials	X	-	-
Client's Requirement, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)	X	-	-
California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)	X	-	-

Note : # = No Specified Requirement * = No Submitted Information N/A = Not Applicable

REMARKS:

STANDARD TECHNICAL LLP.
F-26, 1ST FLOOR, SECTOR-11, NOIDA
email. lab@standard-technical.com | phone. +91 74281 45627 | web. www.standard-technical.com

Page 4 - 6

NON-ACCREDITED TEST PARAMETERS

Tests Description	Results	Requirements

1 : CPSIA Section 101, Total Lead in Substrate Materials

CPSC-CH-E1002-08.3: 2012 (Non-Metal), Equipment used: Atomic Absorption Spectroscopy (AAS).

Specimen	001 (mg/kg)	002 (mg/kg)	Limit (mg/kg)
Total Lead (Pb)	ND	ND	100

Note*:* mg/kg =Milligrams per kilogram
      LT = Less than
      ND = Not detected (Reporting Limit = 20 mg/kg)

2 : California Proposition 65, Total Lead in Substrate Materials

CPSC-CH-E1002-08.3: 2012 (Non-Metal), Equipment used: Atomic Absorption Spectroscopy (AAS).

Specimen	001 (mg/kg)	002 (mg/kg)	Limit (mg/kg)
Total Lead (Pb)	ND	ND	100

Note*:* mg/kg =Milligrams per kilogram
      LT = Less than
      ND = Not detected (Reporting Limit = 20 mg/kg)

Remark: The specification is quoted from client's requirement.

3 : Client's Requirement, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)

Based on CPSC-CH-C1001.09.4: 2018, Equipment used: Gas Chromatography with Mass Spectrometry (GC-MS).

Test Item	CAS No.	Specimen 001 (mg/kg)	002 (mg/kg)	Limit (mg/kg)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	1000
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 / 68515-48-0	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0, 68515-49-1	ND	ND	1000

STANDARD TECHNICAL LLP.
F-26, 1ST FLOOR, SECTOR-11, NOIDA
email. lab@standard-technical.com | phone. +91 74281 45627 | web. www.standard-technical.com

Page 5 - 6

NON-ACCREDITED TEST PARAMETERS

Tests Description	Results	Requirements

4 : California Proposition 65, Phthalates – (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Based on CPSC-CH-C1001.09.4: 2018, Equipment used: Gas Chromatography with Mass Spectrometry (GC-MS).

		Specimen No		
		001	**002**	
Test Item	**CAS No.**	**(mg/kg)**	**(mg/kg)**	**Limit (mg/kg)**
Dibutyl phthalate (DBP)	84-74-2	ND	ND	1000
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	1000
Di-(2-ethylhexyl) phthalate (DEHP)	117-81-7	ND	ND	1000
Diisononyl phthalate (DINP)	28553-12-0 / 68515-48-0	ND	ND	1000
Diisodecyl phthalate (DIDP)	26761-40-0, 68515-49-1	ND	ND	1000
Di-n-hexyl phthalate (DnHP)	84-75-3	ND	ND	1000

Note: mg/kg =Milligrams per kilogram =0.0001% m/m (Percent by mass)
  LT = Less than
  ND = Not detected (Reporting Limit = 150 mg/kg)

Remark: The specification is quoted from client's requirement.

END OF THE TEST REPORT

STANDARD TECHNICAL LLP.
F-26, 1ST FLOOR, SECTOR-11, NOIDA
email. lab@standard-technical.com | phone. +91 74281 45627 | web. www.standard-technical.com